











- SIZE 46" x 7" (1164mm x 194mm) 3 layer elastic acrylic matte w/ ceramic bead varnish, UV cured
 Moisture resistant, high-density fiberboard
 JointShield® edge sealing system
 Integrated cork underlay I mm thickness
 20 Year Limited Residential Wear

VINYL CORK





Amazon



Antique



References

This specification applies to all APC Cork's references of floating floor panels with a vinyl surface layer, from the collection with the trade name VINYL CORK.

Definition

Panels consisting of a compact high density fiberboard layer, a bonded surface layer of Luxury Vinyl and a back layer of soft agglomerated cork as underlay.

The core material (substrate) is tongued and grooved with a special profile design (UNICLIC®) to allow the panels to be assembled together mechanically, without the use of glue.

The edges of each panel elements are protected by "JointShield". Using a patented coating technology, a moisture-repellent agent is constantly applied to the entire cross-section of the profile.

Materials

Surface:

2mm thickness luxury vinyl with 0.33mm wear.

Substrate: High density fiberboard with very low formaldehyde content (E1) and high moisture


resistance properties.

Backing:

Insulating soft agglomerated cork sheet with Microban® antibacterial protection.

Adhesive:

Solvent-free modified PVA emulsion (D3 grade). Impregnating oil-paraffin wax composition.



Classification based on intensity of use

Classification of the floor panels in accordance with the scheme established in EN 685.

Level of use	Class	Symbol	
Domestic	23 Heavy		
Commercial	32 General		



Additional Properties

Characteristic	Symbol	Requirement	Test method
Thickness of wear layer		0.33 mm	EN 429
Mass per unit area		Average 9.020 g/m ²	EN 430
Apparent density		Average 950 Kg/m ³	EN 672
Locking strength	 ← → 	F _{long} > 4 kN / m F _{short} >6 kN / m	Internal
Abrasion resistance		< 5 mg/100 cycles	EN 660-2
hermal resistance		0.10 m ² .K/W	EN 14041 EN 12667
lectrical behaviour	7	Antistatic floor covering (vinyl surface) The body voltage shall not exceed 2.0 kV	EN 14041 EN 1815

Packing

Vinyl Cork floating floor panels shall be dispatched in cardboard trays wrapped in shrinking foil, providing suitable protection for normal transport and storage conditions. Packages shall be marked with identifying information by a label and/or inkjet printing and palletized. Each pallet is over strapped and wrapped with stretch film.

		Pac	kage		
Planks per pack	m² per pack	Packs per pallet	m² per	Weight per	Weight per
8	1.81 m ²	56	101.36 m ²		930 Kg
The same and the s		pack pack	Planks per pack pack per pallet Packs per pallet	pack pack pallet pallet	Planks per pack Packs per pallet Pack per pack Planks per pack Packs per pallet Pack Weight per pack



Specification Requirements

Characteristic	Symbol	Requirement	Test method
Length and width measured at the surface layer		1164x194 mm ± 0.10%	EN 427
Overall thickness	(v	9.5 mm ± 0.20 mm	EN 428
Squareness Straightness measured at the surface layer		< 0.3 mm < 0.2 mm	EN 427
Flatness of the panel Length - Concave / Convex Width - Concave / Convex		≤ 0.1 % / ≤ 0.5 % ≤ 0.05 % / ≤ 0.1 %	EN 14085 Annex A
Openings between panels Average Individual values		≤ 0.10 mm ≤ 0.15 mm	EN 14085 Annex B
Height difference between panels Average Individual values		≤ 0.15 mm ≤ 0.20 mm	EN 14085 Annex B
Residual indentation		≤ 0.25 mm	EN 433
Dimensional variation caused y changes in tmospheric humidity	K Z K	≤ 0.15 %	EN 669 Annex C

Safety Properties

Characteristic	Symbol	Requirement	Test method
Reaction to fire	B _H -s1	Class B _{fl} – S1	EN 14041 EN 13501-1
Formaldehyde emission	Е1	Formaldehyde Class E1 Release ≤ 3.5 mg/m²h	EN 14041 EN 717-2
Slip resistance	The state of the s	Technical class DS. (vinyl surface) dynamic coefficient of friction ≥ 0.30	EN 14041 EN 13893



Supplementary information

Information on laying and maintenance of vinyl cork floating floor panels can be obtained at our website at www.APCCORK.com.

Technical Features





Industry leading patented $\mathsf{UNICLIC}^{\circledcirc}$ locking system and GFIX join performance.



The edges of each panel elements are protected by "JointShield". Using a patented coating technology, a moisture-repellent agent is constantly applied to the entire cross-section of the profile.



Embedded antibacterial and fungus protection using Microban® antibacterial technology.



Indoor air quality certification for low-emitting interior building materials.



Formaldehyde-free agglomeration technology.

Normative references

EN 427	Resilient floor coverings - Determination of the side length and the squareness and straightness of tiles
EN 428	Resilient floor coverings - Determination of the overall thickness
EN 429	Resilient floor coverings. Determination of the thickness of layers
EN 430	Resilient floor coverings - Determination of mass per unit area
EN 433	Resilient floor coverings - Determination of mass per unit area
EN 660-2	Resilient floor coverings - Determination of residual indentation after static loading Resilient floor coverings. Determination of wear resistance. Frick-Taber test
EN 669	Resilient floor coverings - Determination of Wear resistance. Frick-Taber test
	Resilient floor coverings - Determination of dimensional stability of linoleum tiles caused by changes in atmospheric humidity
EN 672	Resilient floor coverings - Determination of apparent density of agglomerated cork
EN 685	Resilient floor coverings - Classification
EN 12104	Resilient floor coverings - Specification for cork floor tiles
EN 14085	Resilient floor coverings - Specification for panels for loose laying
EN 14041	Resilient, textile and laminate floor coverings - Essential characteristics
EN ISO 140-8	Acoustics Measurement of aguad issued in the interest of aguad issued in the interest of aguad issued in the interest of aguard issu
	Acoustics. Measurement of sound insulation in buildings and of building elements. Laboratory measurements of the reduction of transmitted impact noise by floor coverings on a heavyweight standard floor



Product made on a production line certified ISO 9001.



CE The product holds the CE mark for safety and energy-saving performance